

BUTYL EIGHT[®] Liquid Accelerator

January 6, 2014

RTV Product Code: 07708
Composition: Activated dithiocarbamate
Physical State: Reddish brown liquid

	<u>Specification</u>	<u>Test Method</u>
*Density at 25°C	0.98 – 1.02 Mg/m ³	T-9A
*Dithiocarbamate Content	33.0 – 37.5%	T-978
*Flash Point, CCC	34°C minimum	ASTM D6450

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

pH 8.0

Solubility - Moderately soluble in gasoline. Very soluble in acetone, toluene, chloroform, alcohol, and carbon disulfide.

*Certified Property

Uses – Accelerator for room temperature vulcanization of spread solvent cements, calendered and extruded stocks. Accelerated stocks should be used within 8 to 12 hours to prevent pre-cure.

BUTYL EIGHT is a registered trademark of R.T. Vanderbilt Holding Company, Inc. and/or its respective wholly owned subsidiaries.