

DURAX® (CBS) Accelerator

March 24, 2004

RTV Product Code: **20850**
Composition: N-cyclohexyl-2-benzothiazolesulfenamide
Physical State: Off-white to tan powder

	<u>Specification</u>	<u>Test Method</u>
*Ash Content	0.5% maximum	GB 11409.7
*Assay	95.0% minimum	QB 2001.05
*Moisture at 60°C	0.4% maximum	GB 11409.4
*Initial Melting Point	97°C minimum	GB 11409.1

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Density at 20°C 1.28 Mg/m³

Solubility - Soluble in chloroform, ether and toluene. Insoluble in water.

*Certified Property

Uses – Non-discoloring, primary, delayed-action accelerator for NR and synthetic rubbers. Safe at processing temperatures, fast at curing temperatures.

Standard Container – 55.1 pound multi-wall paper bag