



Vanderbilt Chemicals, LLC

A Wholly Owned Subsidiary of R.T. Vanderbilt Holding Company, Inc.

30 WINFIELD STREET, P.O. BOX 5150, NORWALK, CONNECTICUT 06856-5150 • (203) 853-1400

Fax (203) 853-1452 • Internet Address: www.vanderbiltchemicals.com

Specification

NACAP® Corrosion Inhibitor

March 21, 2018

RTV Product Code: 29409

Composition: 50% aqueous solution of sodium 2-mercaptobenzothiazole

Physical State: Light amber liquid

| | <u>Specification</u> | <u>Test Method</u> |
|--------------------------|----------------------|--------------------|
| *Assay | 49.5-50.5% | 1220A |
| *Color, Gardner | 10 maximum | 90018 |
| *Free Alkalinity as NaOH | 0.5% maximum | 1220A |

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate on Analysis.

Density at 25°C 1.27 Mg/m³

Solubility - Soluble in water, alcohol and glycol.

Storage: Product will oxidize if exposed to air for prolonged periods, resulting in the precipitation of solids.
Product may FREEZE or CRYSTALLIZE without Permanent Damage: Warm Slowly to room temperature and stir well to obtain a homogenous product.

*Certified Property

Uses - Corrosion inhibitor for nonferrous metals.

The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Chemicals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent or to violate any federal, state or local law or regulation.