

BUTYL TUADS[®] Accelerator

March 9, 2015

RTV Product Code: 40850
Composition: Tetrabutylthiuram disulfide
Physical State: Dark amber liquid

	<u>Specification</u>	<u>Test Method</u>
*Density at 25°C	1.05 – 1.07 Mg/m ³	T-9A
*Assay	95.0% minimum	LC-32

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Heat Loss at 60 – 65°C	3.0% maximum	T-1A
------------------------	--------------	------

NOTE: If crystals are present upon receipt, heat to 45 - 55°C to liquefy.

*Certified Property

Uses: Sulfur donor accelerator for soluble cure systems in natural and polyisoprene rubbers. Used in conjunction with AMYL LEDATE[®] in EPDM.

TUADS is a registered trademark of R.T. Vanderbilt Holding Company, Inc. and/or its respective wholly owned subsidiaries.