

VISTAMAXX™

Specialty Elastomers
Effective December 15, 2006

Vistamaxx 3000

Sales Specifications

Property	Test Method ¹	Unit	Value
Melt Flow Rate (230°C, 2.16 kg)	ASTM D 1238	Gm/10 min.	8 ± 2
Ethylene Content	ASTM D 3900 A or B	wt %	11.0 ± 1.0
Color, Hunter B	ASTM D 6290	Hunter B	2 max.

¹ ExxonMobil test methods are available upon request