

VISTAMAXXTM

Specialty Elastomers
Effective December 5, 2007

Vistamaxx 6202

Sales Specifications

Property	Test Method ¹	Unit	Value
Melt Flow Rate (230 C, 2.16 kg)	ASTM D 1238	Gm/10 min.	20 ± 4
Ethylene Content	ASTM D 3900 A or B	wt %	15 ± 1
Color, Hunter B	ASTM D 6290	Hunter B	2 max.

¹ ExxonMobil test methods are available upon request