



Neoprene GW M2

TECHNICAL INFORMATION – March 2017

Denka Neoprene GW is a sulfur modified polychloroprene stabilized with a thiuram disulfide.

Physical Form	Chips
Color	Amber light yellow to tan
Specific Gravity at 25/4°C, ASTM D7920-66 (1979)	1.23
Mooney Viscosity, ML 1+4 at 212 °F [100 °C] GW M2	37 – 49
Crystallization Rate	Medium
Storage Stability	Fair. May undergo viscosity change during storage and become more scorchy.

* These data are presented to describe Neoprene GW and are not intended to serve as specifications.

Processing and Performance Features

- Rapid Polymer Breakdown**
 Neoprene GW “breaks down”, or softens, under the mechanical shear imposed during mixing to produce smooth-processing compounds having good building tack.
- Fast Cure Rate Without Accelerators**
 Compounds of Neopren GW cured with metal oxides alone have excellent processing safety, yet cure rapidly. Although not required, cure accelerators can be used and are advantageous for some applications.
- Vulcanizates Resistant to Flexing and Other Dynamic Stress**
 Properly compounded vulcanizates of Neoprene GW have high resilience, tear strength, and flex cracking resistance.

Handling Precautions

Neoprene GW has no known health hazards. However, it should be handled in accordance with good industrial hygiene practices. For additional information, read Denka Performance Elastomer LLC reference “ Guide for Safety and Handling and FDA Status of Neoprene Solid Polymers”, and observed the precautions noted therein.

The compounding ingredients used with Neoprene GW to prepare finished products may present health hazards in handling and use. Before proceeding with any compounding work, consult and follow label directions and handling precautions from supplies of all ingredients. Read and heed the product labels.

Neoprene can accumulate a static charge during shipping, unloading, conveying, or pouring from the bag. To avoid hazards associated with a static electric discharge, provide adequate grounding of equipment and personnel while handling Neoprene GW in the vicinity of flammable vapors or dusts. See National Fire Protection Association (NFPA) RP77 “Recommended Practice on Static Electric.”

Information on European Union Dangerous Preparations Directive 1999/45/EC related to Colophony Skin Sensitizer

Colophony is classified as a skin contact sensitizer under European Union Dangerous Preparations Directive 1999/45/EC effective July 30, 2002. This Directive requires labeling of products that contain colophony at levels equal to or greater than 0.1% (refer to the Directives for specific details). Solid (dry type) Neoprene adhesives grade products manufactured by Denka Performance Elastomer LLC contain about 4% colophony (CAS No. 8050-09-7). Toxicological tests have demonstrated that dry Neoprene is not a skin sensitizer. Because of this testing, dry Neoprene polymer is not subject to mandatory labeling under the above Directive despite the presence of the colophony. However, when these Neoprene adhesive grade products are dissolved in organic solvents, the colophony may still be present at concentrations up to 0.8% depending on the solids content of the solutions. In the absence of data showing the adhesive is not a skin sensitizer, the adhesive could be subject to the above EU regulation.

We recommend that manufactures and marketers of adhesive solutions based on Denka Performance Elastomers' Neoprene (dry type) adhesive grade products determine whether the colophony level is above 0.1%. If the manufactured preparation has a colophony content of less than 0.1% it will not be subject to mandatory labeling (provided no other constituents necessitate mandatory labeling). Manufactured preparations that contain higher colophony contents will require the labeling and/or container notices described in the Directive.

Contact Denka at the following location:

Denka Performance Elastomer LLC,
560 Highway 44
LaPlace, LA70068
Telephone: +1-985-536-7400
Email: sales@denka-pe.com

The information set forth herein is furnished free of charge and is based on technical data that Denka Performance Elastomer believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on any patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your Denka Performance Elastomer customer service representative.

Denka Logo is a registered trademark of Denka Company Limited.

The Denka logo consists of the word "Denka" in a bold, blue, sans-serif font. The letter "D" is significantly larger than the other letters and has a white outline. The letters "e", "n", "k", and "a" are smaller and solid blue.